



PRES-ON®
FOAM TAPES



P9200 SERIES

EPDM Foam Tape: Closed Cell,
Soft Density, with High Performance Acrylic Adhesive on One Side.

FEATURES and BENEFITS: • High Performance Acrylic Adhesive for Durable Bond • Closed Cell Foam • Excellent Temperature Range • Excellent Resistance to UV, Ozone, Oxidation, Acid, Chemicals and Weathering •

FOAM SPECIFICATIONS: • ASTM D1056-07 2A1 • ASTM D1056-68 RE41 • ASTM D1056 F2, M • ASTM D6576-07 Type II B, C Soft / Med • FMVSS-302 • UL157, UL48, UL50, UL50E, UL508 - Listed

PROPERTIES	TEST METHOD	RESULT
COLOR	VISUAL*	BLACK
FINISH	VISUAL*	SMOOTH
WIDTH	VISUAL MEASUREMENT**	40" (custom slit widths available)
THICKNESS	VISUAL MEASUREMENT**	.063", .125", .188", .25", .375", .50"
DENSITY	ASTM D1056	3-6 PCF
COMPRESSION DEFLECTION	ASTM D1056	2-5 PSI
COMPRESSION SET (MAX)	ASTM D1056	40%
WATER ABSORPTION (MAX)	ASTM D1056	5%
TEMPERATURE RANGE	ASTM D1056 PRES-ON PTM-2	FOAM: -70°F--+220°F ADHESIVE: -20°F--+200°F
TENSILE STRENGTH, psi	ASTM D412	40 psi
ELONGATION, %	ASTM D412	175%
ADHESIVE PEEL ADHESION	PSTC-1	Steel immediate, 3.5 lbs/inch width or foam tear Steel after 24 hours, 7.0 lbs/inch width or foam tear Polystyrene immediate, 5.0 lbs/inch width or foam tear Polystyrene after 24 hours, 7.0 lbs/inch width or foam tear Powder Paint immediate, 3.5 lbs/inch width or foam tear Powder Paint after 24 hrs, 3.5 lbs/inch width or foam tear
STATIC SHEAR @ 72°F 1 x 1 x 500 grams STATIC SHEAR @ 72°F 1 x 1 x 100 grams	PSTC-7	Immediate 200 hours minimum

*Color and Finish may vary based on production lot.

**Measurement tolerances vary based on thickness and width, contact Pres-On for specific tolerance to your finished product

APPLICATION NOTES: Ensure bonding surfaces are well unified, clean, dry, and free of dirt and oils. Apply firm and even pressure to improve adhesive-to-surface contact. Allow proper temperature and time to enhance bond strength.

For Terms and Conditions: visit <https://www.preson.com/terms-conditions/>

Adhering to a higher standard™



Find the right product for your application today! Call Pres-On at 800-323-7467.
visit www.preson.com, or email sales@preson.com.

2600 E. 107th Street | Bolingbrook, IL 60440
630-628-2255 | www.preson.com