




PRES-ON®

SEPARATOR PADS



Removable adhesive backed and non-adhesive separator pads available in a range of custom shapes and sizes, as well as variable combinations of cork, felt and foam, providing the flexibility required for protecting delicate surfaces.

Pres-On separator pads are ideal for protecting fragile glass, windows, doors, mirrors, easily scratched metal, paint-coated products and other breakable items from damage by absorbing vibration and reducing slippage during packing, shipping and installation.

| MATERIAL | MATERIAL SPEC | BACKING |
|--|--|--|
| CORK / FOAM  | <u>PRES-ON P10400 SERIES</u> NATURAL GRANULATED CORK DENSITY: 10 LB. TENSILE STRENGTH: 35 PSI COMPRESSION @ 100PSI: 20-35% RECOVERY (after 100 psi): 75% min TEMPERATURE RANGE: -20 to 175F | NO ADHESIVE, CLING FOAM <u>PRES-ON VF5600 SERIES</u> DENSITY: 7 LB. HARDNESS: 25 SHORE 00 TENSILE STRENGTH: 30 PSI COMPRESSION DEFLECTION 1.3 PSI |
| FOAM / FOAM  | <u>PRES-ON PF1600 SERIES</u> CROSS-LINKED PE FOAM DENSITY: 4 LB. TENSILE STRENGTH: 70 PSI COMPRESSION STRENGTH (25% Deflection): 13psi COMPRESSION SET (% of Original Thickness): 16% TEMPERATURE RANGE: -40 to 160 F | NO ADHESIVE, CLING FOAM <u>PRES-ON VF5600 SERIES</u> DENSITY: 7 LB. HARDNESS: 25 SHORE 00 TENSILE STRENGTH: 30 PSI COMPRESSION DEFLECTION 1.3 PSI |
| FELT  | <u>PRES-ON P7300 FELT</u> DENSITY: .31 LBS/SQ YD TENSILE STRENGTH: 39 HARDNESS RANGE: 15-25 SHORE 00 TEMP RANGE: -80 to 200 F | REMOVABLE PSA TYPE: ACRYLIC TEMP RANGE -40 to 175 F |
| FOAM  | <u>PRES-ON PF1600 SERIES</u> CROSS-LINKED PE FOAM DENSITY: 4 LB. TENSILE STRENGTH: 70 PSI COMPRESSION STRENGTH (25% Deflection): 13psi COMPRESSION SET (% of Original Thickness): 16% TEMPERATURE RANGE: -40 to 160 F | REMOVABLE PSA TYPE: ACRYLIC TEMP RANGE -40 to 175 F |
| CORK  | <u>PRES-ON P10400 SERIES</u> NATURAL GRANULATED CORK DENSITY: 10 LB. TENSILE STRENGTH: 35 PSI COMPRESSION @ 100PSI: 20-35% RECOVERY (after 100 psi): 75% min TEMPERATURE RANGE: -20 to 175F | REMOVABLE PSA TYPE: ACRYLIC TEMP RANGE -40 to 175 F |

APPLICATION NOTES: Ensure bonding surfaces are well unified, clean, dry, and free of dirt and oils.

For Terms and Conditions: visit <https://www.preson.com/terms-conditions/>

Adhering to a higher standard™



Find the right product for your application today! Call Pres-On at 800-323-7467.
visit www.preson.com, or email sales@preson.com.

2600 E. 107th Street | Bolingbrook, IL 60440
630-628-2255 | www.preson.com